


Trawl Warps and Purse Wires


DYFORM® starfish

High strength and proven extended ropelife - preventing core corrosion and maintaining design diameter.



6x26 (10/5&5/5/1) Poly Core

Poly Core			
Diameter	Weight	Minimum breaking load	
		Tonnes	kN
mm	Kg/100mtr		
16	103.3	17.1	168
18	129.1	21.6	212
20	159.7	26.7	262
22	191.7	32.3	317
24	224.8	38.5	377
26	271.5	45.1	443
28	317.4	52.4	514
30	357.3	60.1	590
32	408.8	68.4	671
34	468.2	77.2	757
36	514.5	86.6	849
38	578.6	96.4	946
40	635.2	106.9	1048
42	700.3	117.8	1155
44	768.5	129.3	1268




6x26 (10/5&5/5/1) IWRC

Steel Core			
Diameter	Weight	Minimum breaking load	
		Tonnes	kN
mm	Kg/100mtr		
16	115.5	19.1	187
18	145.3	24.1	237
20	183	29.8	292
22	216.6	36.0	353
24	254.7	42.9	420
26	307.2	50.3	493
28	351.7	58.4	572
30	403.8	67.0	657
32	461.1	76.2	748
34	527.2	86.0	844
36	599.4	96.5	946
38	661.1	107.5	1054
40	725.4	119.1	1168
42	799.3	131.3	1288
44	838	144.1	1413


DYFORM®

High strength - smooth periphery for reduced pulley wear.



6x26 (10/5&5/5/1) Poly Core

Poly Core			
Diameter	Weight	Minimum breaking load	
		Tonnes	kN
mm	Kg/100mtr		
16	103.3	17.1	168
18	129.1	21.6	212
20	159.7	26.7	262
22	191.7	32.3	317
24	224.8	38.5	377
26	271.5	45.1	443
28	317.4	52.4	514
30	357.3	60.1	590
32	408.8	68.4	671
34	468.2	77.2	757
36	514.5	86.6	849
38	578.6	96.4	946
40	635.2	106.9	1048
42	700.3	117.8	1155
44	768.5	129.3	1268



6x26 (10/5&5/5/1) IWRC

Steel Core			
Diameter	Weight	Minimum breaking load	
		Tonnes	kN
mm	Kg/100mtr		
16	115.5	19.1	187
18	145.3	24.1	237
20	183	29.8	292
22	216.6	36.0	353
24	254.7	42.9	420
26	307.2	50.3	493
28	351.7	58.4	572
30	403.8	67.0	657
32	461.1	76.2	748
34	527.2	86.0	844
36	599.4	96.5	946
38	661.1	107.5	1054
40	725.4	119.1	1168
42	799.3	131.3	1288
44	876.3	144.1	1413



Figures shown are for guidance purposes only. For details specific to your requirement please contact Bridon